DLG Test Report 7225

S

trilene twin

trilen® twin 💿

joachim behrens scheessel gmbh S.A. Silofolie trilen[®] 400



CONTINUOUS MONITORING

DLG Test Report 7225

trilen® twin 🖗

= 6

www.DLG-Test.de

Overview

The DLG QUALITY SEAL for operating equipment and consumables encompasses products, which are subjected to extensive testing of their value-determining and advertised characteristics. The tested criteria and the requirements to be fulfilled are specified by independent commissions and are designed – over and above legal requirements – to prove the product's fitness for purpose, its advertised characteristics and practical requirements.



Testing contents and requirements are developed further by the responsible specialist departments of the DLG e.V. in line with the applicable legislation, as well as with technical and scientific progress. Successful testing is concluded with the assignment of the DLG QUALITY SEAL. The approved products are then published. Other criteria were not investigated.

Test results

DLG QUALITY PROFILE	Requirement	Evaluation*
Film dimensions	\geq nominal length, \geq 98% nominal width	\checkmark
Film thickness	$0,076 \le d \le 0,084 \text{ mm}$	\checkmark
Material condition	evenly coloured, free of streaks and pores	\checkmark
Tearing force in new condition	longitudinally, transversely, over folds: \geq 25 N/cm	\checkmark
Elongation of tears in new condition	longitudinally, transversely, over folds: $\geq400~\%$	\checkmark
Tear resistance in new state	longitudinally, transversely, over folds: \geq 17 MPa	\checkmark
Dart drop resistance in new condition	compliance with the manufacturer's declaration	\checkmark
Elongation of tear transversely after acid storage	reduction: \leq 15 %	\checkmark
Tear resistance transverse after acid storage	reduction: < 10 %	\checkmark
Elongation of tears transversely after aging (weathering)	>350%; reduction in new condition: $<30%$	\checkmark
Change in size after warm storage after aging	longitudinal: $\leq 2\%$ /transverse: $< 2\%$	\checkmark
Oxygen permeability in 0,2 bar	< 250 cm³/(m² · d)	\checkmark

* Evaluation range: requirements fulfilled (\checkmark) / requirements not fulfilled (\bigstar)

Manufacturer and contact information

Manufacturer and Applicant

joachim behrens scheessel gmbh, Celler Straße 60, 27374 Visselhövede, Germany

Contact

Phone +49 (0)4262 2074-0, Fax +49 (0)4262 3009819, service@jbs.gmbh, www.jbs.gmbh



DLG TestService GmbH

Groß-Umstadt location Max-Eyth-Weg 1 • 64823 Groß-Umstadt • Germany Phone: +49 69 24788-600 • Fax: +49 69 24788-690 Tech@DLG.org • www.DLG.org Download of all DLG test reports free of charge at: www.DLG-Test.de